

PCTWORLD INTELLECTUAL PROPERTY ORGANIZATION
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁵ : C09K 3/10, C08K 3/00, 3/22 C09K 21/14, C08L 83/04	A1	(11) International Publication Number: WO 94/11455 (43) International Publication Date: 26 May 1994 (26.05.94)
(21) International Application Number: PCT/GB93/02321 (22) International Filing Date: 11 November 1993 (11.11.93) (30) Priority data: 9223636.3 11 November 1992 (11.11.92) GB (71) Applicant (for all designated States except US): VISPAK LIMITED [GB/GB]; 4 Pomeroy Drive, Oadby Industrial Estate, Oadby, Leicester LE2 5NE (GB). (72) Inventors; and (75) Inventors/Applicants (for US only) : TRAHEARN, Guydo, Rees [GB/GB]; 23 Roy Close, Narborough, Leicester LE9 5DN (GB). HLUCHAN, Wolodymyr, Iwan [GB/GB]; 3 Oakdene Road, West Knighton, Leicester LE2 6JL (GB).		(74) Agent: SMITH, Peter, James; Serjeants, 25 The Crescent, King Street, Leicester LE1 6RX (GB). (81) Designated States: AU, CA, FI, JP, NO, US, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i>
(54) Title: SEALANTS (57) Abstract <p>A fire retarding sealant comprises a silicone resin, a filler, a ceramic fire retardant such as zinc borate, a smoke suppressant such as stearate coated calcium hydroxide, and either aluminium hydroxide or magnesium hydroxide, preferably the former. The sealant is intumescent, and non-setting, and is intended for placement around pipes, cables and service penetrations in walls, floors and ceilings. At the temperatures encountered in fires, the aluminium hydroxide decomposes to form aluminium oxide and steam, the latter causing the sealant to intumesce while being relatively harmless to people (no halogen gases are evolved). The aluminium oxide and zinc borate form a crust on the intumesced sealant, providing a further fire retardant property.</p>		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Licchtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TC	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

TITLE

Sealants

DESCRIPTION

The invention relates to a sealant which is silicone based and has non-setting and fire-retarding and intumescent properties.

It is known that fire retarding sealants may be placed around pipes, cables and service penetrations in walls, floors and ceilings. However, such sealants may prevent access for servicing purposes.

The invention provides a sealant comprising a silicone resin, a filler, a ceramic fire retardant, a smoke suppressant, and either aluminium hydroxide or magnesium hydroxide.

The sealant according to the invention has intumescent properties derived from the aluminium or magnesium hydroxide. Its fire retarding properties are enhanced by the inclusion of the ceramic fire retardant, which is preferably zinc borate. The preferred hydroxide is aluminium hydroxide. At a temperature of about 200°C, this compound decomposes to form aluminium oxide and steam, the latter causing the sealant to intumesce while being relatively harmless to people. The aluminium oxide and zinc borate form a crust on the intumesced sealant providing a further fire retardant property. At the temperatures encountered in fires, the magnesium hydroxide behaves in a corresponding manner.

The sealant according to the invention, being placed in the service penetration, will thus intumesce upon exposure to heat in a fire, effectively sealing any spaces in the penetration which would allow fire and smoke to pass into another contained area. Since the

sealant is non-setting, however, it can be removed after installation for servicing purposes. Furthermore the sealant is solvent free and halogen free and will not evolve halogen gases upon intumescence.

The sealant according to the invention preferably contains a minimum of 30% by weight of the heat-curing silicone resin, and 10 to 20% by weight of filler. The silicone resin used is commercially available as silicone gum. The silicone gum may have a molecular weight of about 250000 to 550000 and a penetration test value of about 600 to 900. Other silicone resins may be used in the compounding of the sealant. Although many fillers could be used, dolomite is preferred on the grounds of whiteness and economy.

The aluminium hydroxide preferably constitutes up to 40% by weight of the sealant. The amount of intumescence increases with the amount of aluminium hydroxide.

The sealant according to the invention may further contain any additives customarily included in such compositions. These may include surfactants, plasticisers, preservatives, pigments, toolability (shaping and forming) improvers and rheology modifiers. So called "high pressure" intumescent products, such as activated graphite and sodium silicate, may also be added.

It is especially preferred to add a luminous pigment such as copper-activated zinc sulphide. This pigment luminesces in the absence of light, and may act as a visual identification of the grade of sealant to building inspectors and fire prevention officers, both on initial and subsequent inspections.

- 3 -

The invention is illustrated by the following Examples:

Example 1

A fire retardant intumescent non-setting sealant was prepared by compounding the following substances in a Narben mixer:

	<u>% by weight</u>
alpha, omega - divinylpolydimethylsiloxane, or alpha, omega - dimethylpolydimethylsiloxane	30.175
Aluminium hydroxide	31.228
Stearate coated calcium carbonate	8.772
Dolomite	17.544
Zinc borate	<u>12.281</u>
	100.000

In this composition, the stearate coated carbonate is a smoke suppressant and rheology modifier to prevent slump of the product. The zinc borate is fire retarding enhancing the fire retardant properties of the compound.

The composition is a non-setting, hand malleable paste capable of extrusion into rope form or custom profiled forms. It had a Smoke Index of 23 as determined according to Naval Engineering Standard 711, Issue 2 and a Toxicity Index of 0.19 as determined by Naval Engineering Standard 713, Issue 3.

The following results have been obtained by testing according to the stated British Standards:

BS 476: Part 6 (1989)	Class '0'
BS 476: Part 7 (1987)	Class '2'
BS 476: Part 20 (1987)	4 hours

- 4 -

ES 6853 (1987) Appendix A - Clause A.9	< 350°C
ES 6853 (1987) Appendix B - Clause B.5.1	Ao 0.029
ES 6853 (1987) Appendix B - Clause B.5.2	Ao(ON)3.20; Ao(OFF)3.55

Example 2

A fire retardant intumescent luminous non-setting sealant was prepared as described in Example 1, but to the following composition:

% by weight

alpha, omega - divinylpolydimethylsiloxane, or alpha, omega - dimethylpolydimethylsiloxane	30.175
Aluminium hydroxide	31.228
Stearate coated calcium carbonate	8.772
Dolomite	15.544
Zinc borate	12.281
Copper activated zinc sulphide	<u>2.000</u>
	100.000

The copper activated zinc sulphide pigment provides luminosity to the composition. The inclusion of the copper activated zinc sulphide does not affect the properties or performance as detailed in Example 1.

- 5 -

CLAIMS

1. A sealant comprising a silicone resin, a filler, a ceramic fire retardant, a smoke suppressant, and an intumescent compound which is either aluminium hydroxide or magnesium hydroxide.
2. A sealant according to claim 1 in which the intumescent compound is aluminium hydroxide.
3. A sealant according to claim 2 containing up to 40% of aluminium hydroxide.
4. A sealant according to any preceding claim in which the ceramic fire retardant is zinc borate.
5. A sealant according to any preceding claim containing at least 30% by weight of the silicone resin.
6. A sealant according to any preceding claim containing from 10% to 20% by weight of the filler.
7. A sealant according to any preceding claim in which the smoke suppressant is stearate coated calcium carbonate.
8. A sealant according to any preceding claim further comprising one or more of a surfactant, a plasticiser, a preservative, a pigment, a toolability improver and a rheology modifier.
9. A sealant according to any preceding claim further comprising activated graphite or sodium silicate as a high pressure intumescent additive.
10. A sealant according to any preceding claim further comprising copper activated zinc sulphide as a luminous pigment.

INTERNATIONAL SEARCH REPORT

Intern. Application No

PCT/GB 93/02321

A. CLASSIFICATION OF SUBJECT MATTER

IPC 5 C09K3/10 C08K3/00 C08K3/22 C09K21/14 C08L83/04

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 5 C09K C08K C04B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
Y	EP,A,0 404 326 (DOW CORNING CORPORATION) 27 December 1990 see the whole document ---	1,2,4,7, 8
Y	EP,A,0 446 157 (RHONE-POULENC CHIMIE) 11 September 1991 see the whole document ---	1,2,4,7, 8
Y	DATABASE WPI Week 8105, Derwent Publications Ltd., London, GB; AN 81-06953D & JP,A,55 152 723 (HITACHI CABLE) 29 November 1980 see abstract --- -/--	1,2,4,7, 8

☒ Further documents are listed in the continuation of box C.☒ Patent family members are listed in annex.

* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

21 February 1994

Date of mailing of the international search report

10. 03. 94

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

Puetz, C

INTERNATIONAL SEARCH REPORT

Inter. Patent Application No

PCT/GB 93/02321

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT		
Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	EP,A,0 337 792 (DOW CORNING CORPORATION) 18 October 1989 see page 3, line 15 - line 21 see claims; example 3 ---	1,7,8
A	DATABASE WPI Week 8321, Derwent Publications Ltd., London, GB; AN 83-50766K & JP,A,58 065 751 (SHINETSU CHEM IND) 19 April 1983 see abstract ---	1-3,5,9
A	EP,A,0 341 876 (MINNESOTA MINING AND MANUFACTURING COMPANY) 15 November 1989 see the whole document ---	1,8,9
A	GB,A,2 193 216 (GENERAL ELECTRIC COMPANY) 3 February 1988 see page 1, line 20 - line 23; claim 1 -----	1

INTERNATIONAL SEARCH REPORT

Information on patent family members

Inter. Appl. No.

PCT/GB 93/02321

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP-A-0404326	27-12-90	US-A- 4962151 JP-A- 3037267	09-10-90 18-02-91
EP-A-0446157	11-09-91	FR-A- 2659342 AU-B- 641731 AU-A- 7269091	13-09-91 30-09-93 12-09-91
EP-A-0337792	18-10-89	US-A- 4889878 AU-B- 611276 AU-A- 3301089 JP-A- 1306487	26-12-89 06-06-91 19-10-89 11-12-89
EP-A-0341876	15-11-89	US-A- 4952615 DE-D- 68911198 JP-A- 2018493	28-08-90 20-01-94 22-01-90
GB-A-2193216	03-02-88	CA-A- 1300777 DE-A- 3720769 FR-A, B 2601958 JP-A- 63041565 US-A- 4833190	12-05-92 11-02-88 29-01-88 22-02-88 23-05-89